

NUOSPERSE® FX 600

Pigment Dispersing Agent

GENERAL INFORMATION

NUOSPERSE FX 600 is a highly effective pigment dispersing agent for use in waterborne industrial coatings, protective coatings, gloss dispersion paints, colorants and also printing inks. The product is a liquid, multi-functional polymer and is free of organic solvents.

CHEMICAL & PHYSICAL PROPERTIES

Appearance 20 °C	clear liquid / slightly hazy liquid
Active content	approx. 25 %
Density, 20 °C (ISO 2811-2)	approx. 1045 kg/m ³
Viscosity, 20 °C (ASTM D 2196)	approx. 1600 mPa.s
pH (ASTM D 1172)	8.5 - 9.5
Colour	colourless to yellowish
Solubility	soluble in water

These are typical properties not to be used for specification purposes.

APPLICATIONS

- The multi-functional structure of **NUOSPERSE FX 600** ensures a strong interaction with a wide range of pigments. **NUOSPERSE FX 600** dispersant is not only strongly adsorbed onto inorganic pigments such as titanium dioxide and iron oxides (yellow, red or black) but also onto organic pigments such as fast red, quinoid magenta, phthalo blue and –green. It is also effective with carbon black and extenders. The strong interaction and the unique polymer structure of **NUOSPERSE FX 600** result in optimised stabilisation of pigments in aqueous systems.
- **NUOSPERSE FX 600** is suitable for use with a wide variety of binders such as baked acrylic dispersions, air-drying alkyds, polyester-melamines, 2-pack epoxies, acrylates, etc.
- **NUOSPERSE FX 600** is also used in pigment concentrates for tinting paints, leather finishes, textiles, plastics, inks, and other similar coatings systems.

KEY PROPERTIES

Feature	Consequence
• Optimised stabilisation against pigment flocculation	- high gloss levels - optimal opacity - consistent quality - improved corrosion resistance
• Improved pigment wetting	- shorter grinding times - cost savings - reduced pigment costs
• Strongly adsorbed on pigment surface	- optimises stability - optimal opacity
• Excellent compatibility with a wide range of binders	- high gloss levels - improved film appearance - high water resistance
• Buffers pH	- consistent quality

INCORPORATION

For maximum efficiency, **NUOSPERSE FX 600** is added prior to the grinding stage. The ideal procedure is to dissolve **NUOSPERSE FX 600** in the aqueous medium before the addition of the pigments and extenders.

LEVELS OF USE

We recommend the following dosage of **NUOSPERSE FX 600** as a starting point:

as a pigment dispersant in paint: 0.5 % to 2.0% on total formulation.

as a pigment dispersant in printing inks: 0.5 to 3.0% on total formulation.

as a dispersant/vehicle in pigment concentrates: 1 to 15% on total weight of the pigment concentrate.

As the composition and production procedures of coatings vary enormously, it is recommended to check applicability in each case separately

continued...

NUOSPERSE® FX 600

HEALTH AND SAFETY

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

SHELF LIFE

NUOSPERSE FX 600 has a shelf life of 3 (three) years from date of manufacture.

QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2018, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

© Trademark of Elementis Specialties, Inc.

V01 Jul 2018

North America

Elementis Specialties, Inc.
469 Old Trenton Road
East Windsor
NJ 08512, USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis UK Ltd.
c/o Elementis GmbH
Stolberger Strasse 370
50933 Cologne, Germany
Tel.: +49 221 2923 2066
Fax: +49 221 2923 2011

Asia

Deuchem (Shanghai) Chemical Co., Ltd.
99, Lianyang Road
Songjiang Industrial Zone
Shanghai, China 201613
Tel.: +86 21 5774 0348
Fax: +86 21 5774 3563