BENGEL[®] 62

Economical rheological additive for invert drilling fluids

GENERAL INFORMATION

BENGEL 62 rheological additive is a cost-effective organobentonite viscosifier and suspending agent for oil–based drilling fluids, invert emulsion drilling fluids and packer fluids.

BENGEL 62 is suitable for drilling fluids with a continuous phase of diesel, crude oil or mineral oil. It imparts to the formulation the temperature stable rheology characteristic of organoclays.

CHEMICAL AND PHYSICAL DATA

Composition	organic modified bentonite clay
Color	light tan
Form	finely divided powder
Specific gravity	1.8
Moisture	7.0% maximum

These are typical properties not to be used for specification purposes.

APPLICATIONS

Viscosifying drilling fluids including: Oil-based drilling muds Invert emulsion muds Packer fluids

Based on: Diesel oil Crude oil Mineral oils

ATTRIBUTES

BENGEL 62 gellant:

- Cost-effectively builds viscosity and yield point
- Suspends weighting materials and other solids
- Improves cuttings carrying capacity and hole cleaning
- Increases emulsion stability
- · Aids control of fluid loss to the formation
- Confers temperature stability to the fluid
- Is not harmful to the environment

INCORPORATION

Good agitation should be used when incorporating **BENGEL 62** into the drilling system. The amount of stirring needed will depend on the temperature of the oil, the O:W, mud weight and emulsifier package. The rate of viscosity build from this organoclay increases with increasing temperature and shear. Circulation downhole after the initial mixing will aid in achieving the full viscosity and yield.

A chemical polar activator is needed to ensure full development of rheological properties. When water is present in the mud, it acts as the activator and a separate activator is not necessary. In all–oil systems, however, or in other fluids where no water is included in the formulation or where water is unwanted, a chemical activator such as methanol or propylene carbonate should be added. Mixing 5% water, by weight, into the activator can enhance efficiency.

The following activators have proved effective for **BENGEL 62** in waterless systems:

Suitable	Use level as percentage
chemical activators	of BENGEL 62 weight
Methanol/water (95/5)	33 %
Propylene carbonate	33 %
Propylene carbonate/water (95/5)	33 %

BENGEL[®] 62

LEVELS OF USE

The level of use depends on the rheological properties needed, and on the type of base oil being used. Pilot trials are recommended to optimize performance before field use.

Typical loadings are:

	Pounds	
<u>Mud Type</u>	<u>per Barrel</u>	<u>Kg/m³</u>
Invert Emulsions		
Diesel Oil	2 - 6	6 - 17
Mineral Oil	5 - 9	14 – 25

Health and Safety Data

Before using this product please consult our Material Safety Data Sheet for information on safe handling.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2019, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Specialties, Inc.

North America Elementis 469 Old Trenton Road East Windsor NJ 08512, USA Tel.: +1 609 443 2500 Fax: +1 609 443 2422

Europe

Elementis UK Ltd. c/o Elementis GmbH Stolberger Strasse 370 50933 Čologne, Germany Tel.: +49 221 2923 2066 Fax: +49 221 2923 2011

Asia

Deuchem (Shanghai) Chemical Co., Ltd. 99, Lianyang Road Songjiang Industrial Zone Shanghai, China 201613 Tel.: +86 21 5774 0348 Fax: +86 21 5774 3563

V01 Aug. 2019

Enhanced Performance Through Applied Innovation