

## Levelol 839

### Leveling Agent

#### GENERAL INFORMATION

**Levelol 839** is an aromatic-free, fluorocarbon modified polyacrylate flow and leveling agent used in solvent based coating.

#### CHEMICAL & PHYSICAL PROPERTIES

Composition	fluorocarbon modified polyacrylate
Appearance	clear liquid
Color	≤ 100 APHA
Non-volatile content	49.0 - 51.0 %
Solvent	propylene glycol monomethyl ether acetate
Viscosity	≤ 50 cP
Refractive Index	1.426 - 1.431 (25 °C)

These are typical properties not to be used for specification purposes.

#### APPLICATIONS

- Baking paints
- Polyurethane
- Epoxy
- Coil coatings
- Acrylic systems

#### KEY PROPERTIES

- Reduce surface tension of coating system, good leveling and recoatability.
- Good substrate wettability, prevent crater, pinhole, and fisheyes defects, obtain excellent smoothness.
- It is light stable, hydrolysis resistant and does not migrate from paint film.
- Good compatibility with most solvent and resins.

#### INCORPORATION

Please test compatibility before use.

#### LEVELS OF USE

0.05 - 0.50 % based on total formulation.

#### HEALTH AND SAFETY

As it contains solvents, the product requires special care in handling.

Avoid any eye and skin contact.

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

#### STORAGE RECOMMENDATIONS

Keep away from sources of ignition and heat, as well as container tightly closed in a dry and well-ventilated place.

Stored between 0 °C to 40 °C.

#### SHELF LIFE

**Levelol 839** has a shelf life of 2(two) years from date of manufacture.

#### QUALITY ASSURANCE

Quality system at the site manufacturing this product complies with and is certified to ISO 9001 quality standards.

*NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.*

© Copyright 2022, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

© Trademark of Elementis Specialties, Inc.

V01 Jul. 2022

#### North America

Elementis  
469 Old Trenton Road  
East Windsor  
NJ 08512, USA  
Tel.: +1 609 443 2500  
Fax: +1 609 443 2422

#### Europe

Elementis UK Ltd.  
c/o Elementis GmbH  
Stolberger Strasse 370  
50933 Cologne, Germany  
Tel.: +49 221 2923 2066  
Fax: +49 221 2923 2011

#### Asia

Deuchem (Shanghai) Chemical Co., Ltd.  
99, Lianyang Road  
Songjiang Industrial Zone  
Shanghai, China 201613  
Tel.: +86 21 5774 0348  
Fax: +86 21 5774 3563