

# RHEOLATE® RX 04A

# Hydrophobically Modified Alkali-Swellable Emulsion (HASE) Rheological Modifier

### **GENERAL INFORMATION**

RHEOLATE® RX 04A is an acrylic thickener, low to medium viscosity, with excellent thickening efficiency in the high shear rate range. It can be used with a low shear rate thickener. When used together, it is designed to replace cellulosic thickeners with technical advantages.

Hydrophobically modified alkali swellable thickener was developed with the highest technology for waterborne systems.

RHEOLATE® RX 04A is an efficient thickener for systems formulated with acrylic emulsions, styrene acrylics, acrylic vinyl, vinyl maleates and VeoVa.

#### **PHYSICAL PROPERTIES**

Appearance	Milkey white liquid
Non-volatile content (%)	24 - 26
Volatile Material (%)	Water 74 a 76
Specific Gravity	1.03 to 1.07 (water=1)
Solubility in water	Unlimited
Steam density (Air = 1)	<1 ref. water
Boiling Point	212° F /100°C
Viscosity (Cps) max	15
Evaporation rate	<1 ref. water
рН	3,0- 4,5
T1 ( ) ( )	

These are typical properties not to be used for specification purposes.

### **APPLICATIONS**

- Waterborne Decorative Coatings
- · Finishes matte, semi-gloss and gloss
- Preferably for Systems: Acrylics, Styrene Acrylic systems, Vinyl Acrylics, Acrylic Maleates and VeoVa
- Waterborne Adhesives and sealants
- Waterborne inks

## **KEY PROPERTIES**

Superior performance and appearance when compared to cellulosic modifiers.

Provides medium thickening capacity.

Newtonian behavior giving high transfer during application.

Easy to handle.

High shelf life stability.

High resistance to microbial spoilage.

#### INCORPORATION

RHEOLATE® RX 04A it is an expandable alkali thickener and requires that the pH be adjusted to achieve maximum performance and efficiency. The paints must be formulated with a pH above 7.0.

It is recommended to dilute **RHEOLATE® RX 04A** with water (3 H2O: 1 RHEOLATE® - maximum ratio) prior to addition, always with stirring.

No pre-neutralization of **RHEOLATE® RX 04A** is required. Adjustment with ammonia or amino methyl propanol for complete activation must be done before addition of **RHEOLATE® RX 04A**.

Due to its high mechanical strength, a part of the product can be added in the dispersion phase, always with a pH above 7.0.

Addition at Letdown is the typical procedure, maintaining adequate stirring and pH should be above 7.0.

#### **LEVELS OF USE**

We recommend the use of 0,5% to 1,5 % by weight. Please run a ladder test to determine the most suitable dosage before use.

Dosage is also changed according to the type of finish to be done, by percentage of system solids and final PVC.

## **HEALTH AND SAFETY**

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

#### STORAGE RECOMMENDATIONS

**RHEOLATE® RX 04A** should be kept above 4°C (40°F). In the event of accidental freezing, thaw gently, spread portion between glass slides and examine for granules. If found, Do Not Use.



# RHEOLATE® RX 04A

Hydrophobically Modified Alkali-Swellable Emulsion (HASE) Rheological Modifier

# **SHELF LIFE**

RHEOLATE® RX 04A has a shelf life of 12 (twelve) months from date of manufacture.

#### **QUALITY ASSURANCE**

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2018, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

Rev. October 2020

América do Norte

Elementis 469 Old Trenton Road East Windsor NJ 08512, EUA Tel.: +1 609 443 2500 Fax: +1 609 443 2422

Europa

Elementis UK Ltd. c/o Elementis GmbH Stolberger Strasse 370 50933 Colônia, Alemanha Tel.: +49 221 2923 2066 Fax: +49 221 2923 2011

Ásia

Deuchem (Shanghai) Chemical Co., Ltd. 99, Lianyang Road Zona Industrial Songjiang Xangai, China 201613 Tel.: +86 21 5774 0348 Fax: +86 21 5774 3563