

Levaslip 876

Leveling Agent

GENERAL INFORMATION

Levaslip 876 is a good compatibility polysiloxane surface additive to provide good substrate wetting, anti-cratering performance, slip and excellent leveling for wood coatings, and general industrial coatings.

CHEMICAL & PHYSICAL PROPERTIES

Composition	modified polysiloxane
Appearance	colorless to slight yellow clear liquid
Non-volatile content	12.0 - 14.0 %
Solvent	xylene / ethylene glycol phenyl ether
Specific gravity	ca. 0.93
Refractive index	1.49 - 1.50 (25°C)

These are typical properties not to be used for specification purposes.

APPLICATIONS

- Solvent-based coatings

KEY PROPERTIES

- To provide good substrate wetting and good anti-crater.
- To reduce coefficient of friction, improves scratch resistance, mar resistance and anti-blocking properties.
- If need to re-coat, please test recoatability.

INCORPORATION

It is recommended to carry out serial test of **Levaslip 876** at various level to obtain optimum dosage.

LEVELS OF USE

0.2 - 0.5 % based on total formulation.

HEALTH AND SAFETY

As it contains solvents, the product requires special care in handling.

Avoid any eye and skin contact.

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

STORAGE RECOMMENDATIONS

Keep away from sources of ignition and heat, as well as container tightly closed in a dry and well-ventilated place.

Stored between 0 °C to 35 °C, above 35 °C may due to slightly haze, but not affect performance.

SHELF LIFE

Levaslip 876 has a shelf life of 18 months from date of manufacture.

QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2018, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

© Trademark of Elementis Specialties, Inc.

V01 Feb. 2018

North America

Elementis
469 Old Trenton Road
East Windsor
NJ 08512, USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis UK Ltd.
c/o Elementis GmbH
Stolberger Strasse 370
50933 Cologne, Germany
Tel.: +49 221 2923 2066
Fax: +49 221 2923 2011

Asia

Deuchem (Shanghai) Chemical Co., Ltd.
99, Lianyang Road
Songjiang Industrial Zone
Shanghai, China 201613
Tel.: +86 21 5774 0348
Fax: +86 21 5774 3563