

FINNTALC M50LV

Functional Extender

GENERAL INFORMATION

FINNTALC M50LV is a hydrated magnesium silicate with chemical formula of $Mg_3Si_4O_{10}(OH)_2$.

Finntalc grades are purified in a cascade of multiple flotation cells. This process results in a tight definition of the talc composition, making this natural product similar to a synthetic chemical. In combination with a precisely controlled particle size distribution, this ensures exact reproducibility in formulations.

APPLICATIONS

- Paints & Coatings: low VOC heavy duty protective coatings with dry film thickness > 150 μm , car repair putties.
- Polyester Putties

KEY PROPERTIES

- Pure, lamellar, coarse particle size talc with reduced oil absorption value, special low viscosity impact, stable colour, very hydrophobic, inert and soft.

INCORPORATION

FINNTALC M50LV can be used as a functional extender to achieve following results:

Reduction of VOC emissions and at the same time improve barrier and anti-corrosion properties of high film thickness protective coatings, allow to increase solid content in putties and at the same time improve sandability, application properties and economy.

LEVELS OF USE

Typical use levels for paints and coatings applications are 35 - 50 % depending upon the application and the desired properties.

HEALTH AND SAFETY

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

STORAGE RECOMMENDATIONS

Store dry.

SHELF LIFE

FINNTALC M50LV has a shelf life of 5 (five) years from the date of manufacture.


QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 certificate, which guarantees that all operations are conducted according to the stipulated standards.

continued...

FINNTALC M50LV

MINERALOGY	Talc (Mg-Silicate)		96	%
	Traces of magnesite, dolomite and chlorite			
	CAS-No. 14807-96-6	EINECS-No. 238-877-9		
CHEMICAL PROPERTIES	MgO	XRF	31	%
	SiO ₂	XRF	59	%
	CaO	XRF	0.05	%
	Al ₂ O ₃	XRF	0.5	%
	Fe ₂ O ₃	XRF	2.6	%
	Fe acid soluble	1mol/L HCl, 100°C	0.2	%
	Loss on ignition	DIN 51081/1000°C	6.1	%
	pH value	ISO 787/9	9.1	
OPTICAL PROPERTIES	Whiteness Ry	DIN 53163	76	%
	ISO brightness R457	ISO 2470	75	%
	Refractive index	Mallard	1.57	
	CIE L*, a*, b*	DIN 6174	90/-0.5/1.4	
	Yellowness index	DIN 6167	2.5	
PHYSICAL PROPERTIES	Top cut D98	Sedigraph, ISO 13317	55	µm
	Median particle size D50	Sedigraph, ISO 13317	24	µm
	Fineness of grind	ISO 1524	140	µm
	Sieve residue	ISO 787/7, 106 µm	0.1	%
	Specific surface area	BET, ISO 4652	1	m ² /g
	Oil absorption	ISO 787/5	22	g/100g
	Abrasion	Einlehner AT 1000	7	mg
	Hardness	Mohs	1	



NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2019, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Mondo Minerals BV.

V01 Mar. 2019

North America
Elementis
469 Old Trenton Road
East Windsor
NJ 08512, USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe
Elementis UK Ltd.
c/o Elementis GmbH
Stolberger Strasse 370
50933 Cologne, Germany
Tel.: +49 221 2923 2066
Fax: +49 221 2923 2011

Mondo Minerals B.V.
Kajuitweg 8
NL-1041 AR Amsterdam
The Netherlands
Tel.: +31 20 4487 453

Asia
Deuchem (Shanghai) Chemical Co., Ltd.
99, Lianyang Road
Songjiang Industrial Zone
Shanghai, China 201613
Tel.: +86 21 5774 0348
Fax: +86 21 5774 3563