

FINNTALC M15C

Functional Extender

GENERAL INFORMATION

FINNTALC M15C is a hydrated magnesium silicate with chemical formula of $Mg_3Si_4O_{10}(OH)_2$.

Finntalc grades are purified in a cascade of multiple flotation cells. This process results in a tight definition of the talc composition, making this natural product similar to a synthetic chemical. In combination with a precisely controlled particle size distribution, this ensures exact reproducibility in formulations.

APPLICATIONS

- Plastics: For automotive cabin and under the hood, appliances, pipes, powdering, profiles, packaging, sheets and furniture.

KEY PROPERTIES

- Pure, lamellar, medium particle size talc, stable colour, very hydrophobic, inert and soft.

INCORPORATION

FINNTALC M15C can be used as a functional extender to achieve following results:

Consistent color, low abrasion and longer tool life. Compacted grades are available for low dust generation and easy handling resulting in higher compounding throughput. Compacted grades are available for low dust generation and easy handling resulting in higher compounding throughput.

LEVELS OF USE

Typical use levels for talc in plastics depending upon the application. Please contact your local sales representative for advice.

HEALTH AND SAFETY

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

STORAGE RECOMMENDATIONS

Store dry.

SHELF LIFE

FINNTALC M15C has a shelf life of 5 (five) years from the date of manufacture.


QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 certificate, which guarantees that all operations are conducted according to the stipulated standards.

continued...

FINNTALC M15C

MINERALOGY	Talc (Mg-Silicate)		97	%
	Traces of magnesite, dolomite and chlorite			
	CAS-No. 14807-96-6	EINECS-No. 238-877-9		
CHEMICAL PROPERTIES	MgO	XRF	31	%
	SiO ₂	XRF	60	%
	CaO	XRF	0.1	%
	Al ₂ O ₃	XRF	0.5	%
	Fe ₂ O ₃	XRF	2.2	%
	Fe acid soluble	1mol/L HCl, 100°C	0.2	%
	Loss on ignition	DIN 51081/1000°C	6.0	%
	pH value	ISO 787/9	9.1	
OPTICAL PROPERTIES	Whiteness Ry	DIN 53163	84	%
	ISO brightness R457	ISO 2470	83	%
	Refractive index	Mallard	1.57	
	CIE L*, a*, b*	DIN 6174	93.0/-0.3/0.9	
	Yellowness index	DIN 6167	1.6	
PHYSICAL PROPERTIES	Top cut D98	Sedigraph, ISO 13317	17	µm
	Median particle size D50	Sedigraph, ISO 13317	4.5	µm
	- Particles < 2 µm		20	%
	Fineness of grind	ISO 1524	50	µm
	Specific surface area	BET, ISO 4652	6	m ² /g
	Oil absorption	ISO 787/5	36	g/100g
	Abrasion	Einlehner AT 1000	5	mg
	Hardness	Mohs	1	
	Tapped density	ISO 787/11	1.0	g/cm ³
	Bulk density	DIN 53468	0.8	g/cm ³
	Moisture	ISO 787/2	0.2	%



NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2019, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Minerals B.V.

V02 Dec. 2019

North America
 Elementis
 469 Old Trenton Road
 East Windsor
 NJ 08512, USA
 Tel.: +1 609 443 2500
 Fax: +1 609 443 2422

Europe
 Elementis UK Ltd.
 c/o Elementis GmbH
 Stolberger Strasse 370
 50933 Cologne, Germany
 Tel.: +49 221 2923 2066
 Fax: +49 221 2923 2011

Elementis Minerals B.V.
 Kajuitweg 8
 NL-1041 AR Amsterdam
 The Netherlands
 Tel.: +31 20 4487 448

Asia
 Deuchem (Shanghai) Chemical Co., Ltd.
 99, Lianyang Road
 Songjiang Industrial Zone
 Shanghai, China 201613
 Tel.: +86 21 5774 0348
 Fax: +86 21 5774 3563