

THIXCIN® E

Rheological Additive

for Organic Systems Based on Non-Polar Solvents and for Powder Coatings

GENERAL INFORMATION

THIXCIN E is a non-hygroscopic organic derivative of castor oil. It is chemically the same as THIXCIN R, but less dusty. In powder coatings it offers a more efficient extruder throughput compared with THIXCIN R.

CHEMICAL & PHYSICAL PROPERTIES

Composition	organic derivative of castor oil
Color / Form	fine white powder
Density at 25°C	1.02 g/cm ³
Ash content	0 %
Melting point	85 °C (185 °F)
Incorporation temperature (in liquid products)	43 - 55 °C (110 - 130 °F)

These are typical properties not to be used for specification purposes.

APPLICATIONS

- Alkyd paints
- Hammer finish paints
- Solvent-free epoxy paints
- Radiator paints
- Textured paints
- Wood stains
- Mastics, caulks and sealants
- Plastisols, organosols
- Underbody sealants
- High-build paints
- Gelcoats and surfacers based on unsaturated polyesters
- Powder coatings
- Cosmetics
- Pharmaceutical

KEY PROPERTIES

- Adds thixotropic body and controls viscosity
- Reduces settling of pigments and extenders
- Controls sag without impairing flow
- Produces optimum levelling in paints
- Controls liquid penetration into porous surfaces
- Has no adverse effect on durability and light-fastness
- Is non-yellowing
- Has excellent package stability
- Improves degassing of powder coatings
- Improves flow and levelling of powder coatings
- Is an excellent binder for tablets, granules and cosmetics pressed powder

INCORPORATION

THIXCIN E rheological additive should be added at the beginning of the dispersion process, preferably by pre-mixing in the solvent/binder or vehicle for about 5 minutes before other components are added.

When incorporating **THIXCIN E**, both a lower and an upper processing temperature must be observed. A minimum temperature of about 43°C (110°F) is necessary to build the thixotropic structure properly. If a temperature of 55°C (130°F) is exceeded, soft gel-like particles may appear on return to room temperature. The presence of aromatic solvents lowers this upper temperature limit. Should this limit be exceeded, the formation of particles can be prevented by mild continuous stirring during cooling to 45°C (113°F) or below.

Incorporation into dry systems is by normal powder blending processes. Full dispersion of **THIXCIN E** in powder coatings is achieved at the extruder stage of production.

Within the prescribed temperature range,

THIXCIN E should be subjected to as much shear as possible during processing. The more intense the dispersing or grinding action, the more pronounced and immediate is the effect.

continued...

THIXCIN® E

LEVELS OF USE

Depending on the type of system involved and on the desired degree of thickening, a typical starting use level is 0.2 % to 0.8 % by weight of the total formulation.

In powder coatings typical use levels are 0.2 % to 2.0 %. Pressed powders, tablets and granules need a level of 0.5 % to 2.0 %.

HEALTH AND SAFETY

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

STORAGE RECOMMENDATIONS

THIXCIN E should be kept in a cool, dry location. Avoid stacking pallets in hot climates.

SHELF LIFE

THIXCIN E has a shelf life of 4 (four) years from date of manufacture.

QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2018, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

© Trademark of Elementis Specialties, Inc.

V01 Aug. 2018

North America

Elementis
469 Old Trenton Road
East Windsor
NJ 08512, USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis UK Ltd.
c/o Elementis GmbH
Stolberger Strasse 370
50933 Cologne, Germany
Tel.: +49 221 2923 2066
Fax: +49 221 2923 2011

Asia

Deuchem (Shanghai) Chemical Co., Ltd.
99, Lianyang Road
Songjiang Industrial Zone
Shanghai, China 201613
Tel.: +86 21 5774 0348
Fax: +86 21 5774 3563