

FINNTALC M05SL

Functional Extender

GENERAL INFORMATION

FINNTALC M05SL is a hydrated magnesium silicate with chemical formula of $Mg_3Si_4O_{10}(OH)_2$.

Finntalc grades are purified in a cascade of multiple flotation cells. This process results in a tight definition of the talc composition, making this natural product similar to a synthetic chemical. In combination with a precisely controlled particle size distribution, this ensures exact reproducibility in formulations.

APPLICATIONS

- **Paints & Coatings:** Thin layer (dry film thickness of 15 - 30 μm) architectural and industrial top coats, tinting pastes and inks.
- **Plastics:** For antiblock, automotive bumpers and cabin, foam, film, nucleation, sheets, packaging, profiles and engineered plastics.

KEY PROPERTIES

- Pure, lamellar talc, fine particle size with narrow particle size distribution. Stable colour, very hydrophobic, inert and soft.

INCORPORATION

FINNTALC M05SL can be used as a functional extender to achieve following results:

Paints & Coatings: Good barrier properties, booster of white opacity, matting of low PVC paints, good outdoor durability, finetuning of rheological properties, efficient pigment spacer.

Plastics: High performance grade in plastics. Good impact properties. Compacted grades are available for low dust generation and easy handling resulting in higher compounding throughput.

LEVELS OF USE

Typical use levels for paints and coatings applications are 5 - 15 % depending upon the application and the desired properties.

Typical use levels for talc in plastics depending upon the application. Please contact your local sales representative for advice.

HEALTH AND SAFETY

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

STORAGE RECOMMENDATIONS

Store dry.

SHELF LIFE

FINNTALC M05SL has a shelf life of 5 (five) years from the date of manufacture.


QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 certificate, which guarantees that all operations are conducted according to the stipulated standards.

continued...

FINNTALC M05SL

MINERALOGY	Talc (Mg-Silicate)		98	%
	Traces of magnesite, dolomite and chlorite			
	CAS-No. 14807-96-6	EINECS-No. 238-877-9		
CHEMICAL PROPERTIES	MgO	XRF	31	%
	SiO ₂	XRF	61	%
	CaO	XRF	0.1	%
	Al ₂ O ₃	XRF	0.4	%
	Fe ₂ O ₃	XRF	2	%
	Fe acid soluble	1mol/L HCl, 100°C	0.1	%
	Loss on ignition	DIN 51081/1000°C	5.4	%
	pH value	ISO 787/9	9.1	
OPTICAL PROPERTIES	Whiteness Ry	DIN 53163	89	%
	ISO brightness R457	ISO 2470	88	%
	CIE L*, a*, b*	DIN 6174	96/-0.25/0.6	
	Yellowness index	DIN 6167	1.0	
PHYSICAL PROPERTIES	Top cut D98	Sedigraph, ISO 13317	7.5	µm
	Median particle size D50	Sedigraph, ISO 13317	2.2	µm
	Fineness of grind	ISO 1524	25	µm
	Specific surface area	BET, ISO 4652	10	m ² /g
	Oil absorption	ISO 787/5	50	g/100g
	Abrasion	Einlehner AT 1000	3	mg
	Hardness	Mohs	1	
	Tapped density	ISO 787/11	0.3	g/cm ³
	Bulk density	DIN 53468	0.2	g/cm ³
	Moisture	ISO 787/2	0.1	%



NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2019, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

® Trademark of Elementis Minerals B.V.

V02 Dec. 2019

North America

Elementis
469 Old Trenton Road
East Windsor
NJ 08512, USA
Tel.: +1 609 443 2500
Fax: +1 609 443 2422

Europe

Elementis UK Ltd.
c/o Elementis GmbH
Stolberger Strasse 370
50933 Cologne, Germany
Tel.: +49 221 2923 2066
Fax: +49 221 2923 2011

Elementis Minerals B.V.
Kajuitweg 8
NL-1041 AR Amsterdam
The Netherlands
Tel.: +31 20 4487 448

Asia

Deuchem (Shanghai) Chemical Co., Ltd.
99, Lianyang Road
Songjiang Industrial Zone
Shanghai, China 201613
Tel.: +86 21 5774 0348
Fax: +86 21 5774 3563