NUOSPERSE[®] FN 270

Pigment dispersing and wetting agent for low VOC waterborne coatings

GENERAL INFORMATION

NUOSPERSE FN 270 is an alkylphenol ethoxide-free and labelling-free, universal nonionic pigment wetting and dispersing agent. It is an effective replacement for nonylphenol-10eo.

CHEMICAL & PHYSICAL PROPERTIES

Appearance 20°C	Clear light yellow liquid
Active content	100%
Odour	Nearly odourless
VOC EPA Method 24	0*
VOC ASTM D6886-03	None detected
Specific gravity	1.003
Viscosity @ 25°C (ASTM D2196)	< 100 mPas
Colour (DIN-EN 1557)	< 3 Gardner
HLB value	approx. 12.5

These are typical properties not to be used for specification purposes.

APPLICATIONS

Decorative and industrial emulsion paints with a wide variety of binder chemistries

KEY PROPERTIES

- Universal and efficient pigment wetting and dispersing properties
- Very low foam generation
- Freeze-thaw stable: remains liquid at 0°C
- Improves paint storage stability
- Improves colorant acceptance and increases tinting strength
- APEO-free and labelling-free
- Zero VOC

INCORPORATION

The optimum dosage, compatibility and performance of **NUOSPERSE FN 270** should be checked in each case individually. However, it is recommended to start by replacing nonylphenol-10eo on a one-to-one basis (as supplied).

LEVELS OF USE

Typically, 0.1 to 0.5% would be used in coating formulations whereas 3 to 12% would be required as a vehicle for a pigment concentrates.

HEALTH AND SAFETY

Before using this product please consult our Safety Data Sheet (SDS) for information on safe handling and storage. The SDS can be found on the company website.

STORAGE RECOMMENDATIONS

Keep containers tightly closed in a cool, well-ventilated room. It is recommended to store **NUOSPERSE FN 270** at temperatures above 0°C. **NUOSPERSE FN 270** might solidify at temperatures below -10°C. If this occurs, **NUOSPERSE FN 270** can be returned to a clear, fully active liquid again simply by storing at room temperature.

SHELF LIFE

NUOSPERSE FN 270 has a shelf life of 3 (three) years from date of manufacture.

QUALITY ASSURANCE

Since 1992 the company is a holder of the ISO 9001 / ISO 9002 certificates, which guarantees that all operations are conducted according to the stipulated standards.

NOTE: The information herein is currently believed to be accurate. We do not guarantee its accuracy. Purchasers shall not rely on statements herein when purchasing any products. Purchasers should make their own investigations to determine if such products are suitable for a particular use. The products discussed are sold without warranty, express or implied, including a warranty of merchantability and fitness for use. Purchasers will be subject to a separate agreement which will not incorporate this document.

© Copyright 2018, Elementis Specialties, Inc. All rights reserved. Copying and/or downloading of this document or information therein for republication is not allowed unless prior written agreement is obtained from Elementis Specialties, Inc.

Trademark of Elementis Specialties, Inc.

North America Elementis 469 Old Trenton Road East Windsor NJ 08512, USA Tel.: +1 609 443 2500 Fax: +1 609 443 2422 Europe Elementis UK Ltd. c/o Elementis GmbH Stolberger Strasse 370 50933 Cologne, Germany Tel.: +49 221 2923 2066 Fax: +49 221 2923 2011 Asia Deuchem (Shanghai) Chemical Co., Ltd. 99, Lianyang Road Songjiang Industrial Zone Shanghai, China 201613 Tel.: +86 21 5774 0348 Fax: +86 21 5774 3563

V01 Aug. 2018

www.elementis.com